



BST Safety Glasses | PE7SG01DB



Introducing the BST Safety Glasses

These metal detectable & x-ray visible safety glasses are designed specifically for use in the food industry, where minimising the risk of foreign body contamination is of the highest priority.

The BST Safety Glasses are manufactured using Food Grade ABS which is optimised for metal and x-ray detection in the food and pharmaceutical industries.

The glasses feature adjustable arms, once set to your size it's advisable to leave at the set size. One pair of glasses per user is also recommended, we don't advise sharing PPE items.

Safety Glasses Advantages

- ✓ Detectable by in-line metal detection systems & x-ray inspection systems
- ✓ Compliant with EN 166:2001
- ✓ Gives protection against high speed particles
- ✓ Reduces the risks associated with eye hazards
- ✓ Feature adjustable arms
- ✓ Compliant with EU including mandatory EU migration test standards
- ✓ Can be used as part of HACCP and BRC procedures
- ✓ Displays due diligence in the prevention of foreign body contamination

Product and Packaging Information

Single Pair Code	PE7SG01DB	Pack Weight	0.35kg
Pack of 12 Code	PE7SG01DB12	Pack Weight	4.2kg
Frame Colour	Blue	Frame Material	Detectable ABS
Dimensions	52mm x 140mm	Detectability	Metal Detectable (Frames)
Ocular Material	Polycarbonate	Commodity Code	90049010

Safety Certificates / Approvals

EU Compliant	BRC Compliant	ISO 9001:2015
--------------	---------------	---------------



Food Contact Status

Hereby we declare that the materials ABS are manufactured in line with the relevant requirements of 2023/2006/EC as amended by Commission Regulation (EC) 282/2008, on good manufacturing practice (GMP) for materials and articles intended to come into contact with food. The raw materials used in the manufacturing process of the above mentioned materials meet the relevant requirements of EU Framework Regulation 1935/2004 on materials and articles intended to come into contact with food.

The monomers, starting substances and additives used are listed in Annex I of the consolidated

Commission Regulation No.10 (2011) as amended by (EU) 321/2011/, (EU) 1282/2011, (EU) 1183/2012, (EU) 202/2014, (EU) 2015/174, (EU) 2016/1416, (EU) 2017/752, (EU) 2018/79, (EU) 2018/213, (EU) 2018/831, (EU) 2019/37, and (EU)2019/1338, respectively, related to Plastic Materials and Articles intended to come into contact with foodstuffs.

The colourant used in the formulation of the ABS is compliant with European Council Resolution AP(89)1 on the use of colourants in plastic materials coming into contact with food, and also with German BfR Recommendations (IX).

Migration Testing

The following overall migration results for Food Grade ABS were obtained using a UKAS accredited laboratory, with overall migration simulants and conditions as detailed in EU Regulation No 10/2011 as amended, on plastic materials and articles intended to come into contact with food.

Sample: ABS-2016/047

Test conditions: Simulants A, B and Iso-octane: 10 days at 40°C 95%v/v ethanol: 2 days at 20°C

Method	EN-1186-3 Migration into 10% v/v Ethanol (Simulant A)	EN-1186-3 Migration into 3% w/v Acetic Acid (Simulant B)	EN-1186-14§ Migration into Iso-octane (Substitute test)	EN-1186-14§ Migration into 95% Ethanol (Substitute test)
Replicate #1	0.4 mg/dm ²	0.8 mg/dm ²	346.7 mg/dm ²	14.5 mg/dm ²
Replicate #2	0.4 mg/dm ²	0.8 mg/dm ²	303.8 mg/dm ²	15.5 mg/dm ²
Replicate #3	0.4 mg/dm ²	0.7 mg/dm ²	318.0 mg/dm ²	14.3 mg/dm ²
Mean Result	0.4 mg/dm ²	0.8 mg/dm ²	322.8 mg/dm ²	14.8 mg/dm ²
EU Limit	10.0 mg/dm ²	10.0 mg/dm ²	10.0 mg/dm ²	10.0 mg/dm ²

#Limit and tolerance are quoted after the application of a fatty food reduction factor of 2 as quoted in EU Regulation 10/2011.

To summarise the overall migration test results, the ABS complies with the overall migration requirements given in EU Regulation 10/2011, as amended, with regards to use with all non-fatty foods, aqueous foods and fatty foods that require a reduction factor of 2 (or greater), as given in EU regulation 10/2011, as amended.

Metal Detectability

The BST safety glasses frames are manufactured from electromagnetically detectable plastic compound. This compound contains evenly dispersed non-toxic detectable additives, making the material detectable by correctly calibrated metal detection systems. Metal detectability performance will vary based on, but not limited to the following factors:

- Calibration Levels
- Product Type (E.g. Wet, Dry, Frozen, Liquid)
- Aperture Dimensions
- Orientation

Orientation is a highly influential factor for the metal detectability of a contaminant that is non spherical, i.e. it will be easier to detect the contaminant when passing in one orientation compared to another - this is known as the orientation effect.

For this reason BST recommend that all our products be thoroughly tested on your metal detection systems by a trained and certified professional. It may be the case that your equipment needs to be re-calibrated in order to reliably detect this product. Such a professional should be available by contacting the manufacturer of your metal detection system.

X-Ray Visibility

In contrast to metal detection, x-ray visibility is determined by material density. For this reason, the material for the glasses frames contain an additional, evenly dispersed, food safe, high density additive. X-ray detection performance will be reduced when small fragments are buried in deeper, denser products - detection will depend on product type and density.

We highly recommend that all our products be thoroughly tested on your x-ray inspection systems by a trained and certified professional. It may be the case that your equipment needs to be recalibrated in order to reliably detect this product. Such a professional should be available by contacting the manufacturer of your x-ray inspection system.

The information provided in this product specification sheet is based on our experience and knowledge to date and we believe it to be true and reliable. This information is intended as a guide for your use of our products, the use of which is entirely at your own discretion and risk. We, BS Teasdale & Son Ltd, cannot guarantee favourable results and assume no liability in connection with the use of our products. © 2020 BS Teasdale & Son Ltd. All Content, Data & Images are owned by BS Teasdale & Son Ltd and are protected by international copyright law.